

Containergard® WY Water Based Sheen

Product Description	A water based acrylic primer/finish specially designed for major OEM suppliers in the Modular Building and related markets.				
Intended Use	- Water based to aid compliance with SED and environmental legislation - Low in VOC's - Use over existing coatings - Good drying properties - Good roller application properties for small repair areas				
Approvals/ Certification	Please consult Axalta Coating Systems				
Finish	Sheen				
Volume Solids	43 ± 2% (varies with colour)				
VOC Content	64 ± 20 g/litre (without water - varies with colour)				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Minimum	60 µm	150 µm	6.6 m²/litre	
	Maximum	90 µm	225 µm	4.4 m²/litre	
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated				
Drying Times	Applied to 75 microns DFT		+10°C	+23°C	+35°C
	Dust Free		2 hr	1 hr	n/a
	Hard Dry		24 hr	16 hr	n/a
	Overcoating*	Minimum	24 hr	16 hr	n/a
		Maximum	Indefinite if clean and sound		
	This is a water based paint. Do not apply below 5°C, temperatures above 10°C are recommended. Temperature will have a marked effect on drying times and susceptibility to damage. Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation.				
Colours	Colours to customers' requirements				
Product Code	20CWY				
SG	1.20-1.30 kg/lit mixed (varies with colour)				
Storage Conditions	Store in dry, cool conditions, away from extremes of temperature. Ensure strict stock rotation is carried out. Water based – protect from frost				
Shelf Life	Minimum 12 months if stored as above in unopened containers				
Flash Point	Above 60°C				

Containergard® WY Water Based Sheen

Issue Date: Nov 2020
Page 2 of 2

Surface Preparation	- All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams - Blast clean to Sa2½ (ISO 8501-1:2007), surface profile 50-75 microns - Where blast cleaning is impractical the surface should be prepared to St2 (ISO 8501-1:2007) taking care to avoid 'polishing' the surface				
Mixing	Must be mixed thoroughly by using a mechanical agitator before use. Agitate periodically to ensure paint remains homogeneous.				
Thinner / Cleaner	Clean water				
Application Conditions	Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Only apply this product when the above conditions can be maintained throughout the critical application and drying/curing process. Paint temperature should ideally be at a minimum of 15°C.				
Application Methods	Method	Airless Spray	Conventional Spray	Brush	Roller
		Yes	Yes	Yes	Yes
	- Airless Spray: output fluid pressure at tip 1500-2000 psi, Tip Size: 9-13 thou (0.23-0.33mm) - Air assisted airless: output fluid pressure at tip 1300-1800 psi, Tip Size: 9-13 thou (0.23-0.33mm) - Thinning of the coating will reduce the build qualities and extend the drying time - Brush/roller – use as supplied but suitable for small areas of touch-up only				
Product Notes	- For improved corrosion resistance on bare steel, it is recommended that this product is applied over a suitable primer - please consult Axalta Coating Systems for advice - If applying over fresh solvent based paint, leave at least 48 hours before applying Containergard WY - As with all water based coatings, sufficient drying time (to remove the water from the applied film) is required before the coating will be water resistant, and able to withstand rain or condensation. Times required will depend on film thickness/humidity/ventilation and temperature during application and initial drying. As a general guide, for typical applications of around 100 µm dft and 15°C, we would suggest the following times are required under good drying conditions: Resistance to light shower - overnight Resistance to heavier rain – 24 hours Full weather resistance – 7 days - Drying times will be extended in colder winter conditions, and particularly where there is limited ventilation/heating during application and initial drying				
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.				

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.