

Bondon 116

Product Description	A two pack epoxy, high solids, surface tolerant primer/undercoat.				
Features & Use	<ul style="list-style-type: none"> • Use as a rust inhibiting primer or undercoat on hand prepared steel, or as a high build patch repair primer under most generic coating types • Excellent anticorrosive protection • Excellent 'wetting' properties for application to a manually prepared steel surface • Good chemical and solvent resistance • Use to upgrade a conventional system to high performance epoxy/polyurethane system • Can overlap onto aged, sound chlorinated rubber, vinyl or alkyd products 				
Approvals/ Certification	Please consult Axalta Coating Systems				
Finish	Semi-gloss				
Volume Solids	82 ± 2%				
VOC Content	150 ± 20 g/litre				
Film Thickness Range And Coverage		Dry Film Thickness	Wet Film Thickness	Theoretical Coverage	
	Minimum	100 µm	122 µm	8.2 m ² /litre	
	Maximum	200 µm	244 µm	4.1 m ² /litre	
Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated					
Drying Times	Applied to 125 microns DFT		+10°C	+23°C	+35°C
	Dust Free		8 hr	6 hr	4 hr
	Hard Dry		24 hr	16 hr	12 hr
	Overcoating	Minimum	18 hr	15 hr	12 hr
		Maximum	12 weeks		
Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation					
Colours	Limited colour range				
Mix Ratio/ Product Code	Base	12116-	4 part by volume		
	Hardener	12115-ACT	1 part by volume		
Pot Life	2 hours at 23°C				
SG	1.41 kg/lit mixed				
Storage Conditions	Store in dry, cool conditions and protect from frost				
Shelf Life	Minimum 12 months if stored as above in unopened containers				
Flash Point	23-60°C				

Bondon 116

<p>Surface Preparation</p>	<ul style="list-style-type: none"> All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination. Where necessary, remove weld spatter and grind smooth all sharp edges and weld seams Blast clean to Sa2½ (ISO 8501-1:2007), surface profile 50-75 microns Where blast cleaning is impractical the surface should be prepared to St2 (ISO 8501-1:2007) taking care to avoid 'polishing' the surface Can be used as a brush or spray applied primer when water abrasive blast cleaning. Allow to dry and lightly wire brush if powdery deposits form 														
<p>Mixing</p>	<p>Mix only in the proportions stated, mixing each component individually then together using a mechanical agitator. Agitate periodically during use to ensure product remains homogeneous.</p>														
<p>Thinner / Cleaner</p>	<p>Axalta Thinner TH500 (formerly called No.5 Thinner)</p>														
<p>Application Conditions</p>	<p>Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Only apply this product when the above conditions can be maintained throughout the critical application and drying/curing process. Paint temperature should ideally be at a minimum of 15°C.</p>														
<p>Application Methods</p>	<table border="1"> <thead> <tr> <th>Method</th> <th>Airless Spray</th> <th>Conventional Spray</th> <th>Brush</th> <th>Roller</th> </tr> </thead> <tbody> <tr> <td></td> <td>Yes</td> <td>No</td> <td>Yes</td> <td>Yes</td> </tr> </tbody> </table>	Method	Airless Spray	Conventional Spray	Brush	Roller		Yes	No	Yes	Yes				
Method	Airless Spray	Conventional Spray	Brush	Roller											
	Yes	No	Yes	Yes											
<ul style="list-style-type: none"> Airless Spray: Output fluid pressure at tip 2000-3000 psi, Tip Size: 13-21 thou (0.33-0.53mm). Brush is preferred over manually prepared bare steel surfaces to assist surface penetration and wetting If applying by roller over blast cleaned steel, there is a tendency to over spread the coating resulting in low film builds. If the film build is too low a second coat should be applied to achieve required film build Refer to Axalta Coating Systems 'Epoxy Application and Curing Notes' 															
<p>Product Notes</p>	<ul style="list-style-type: none"> Overcoating - if overcoating with products other than itself or Bondon 168/169 please consult Axalta Coating Systems for advice. For best results, overcoat within 7 days at 23°C Extend min/max drying and overcoating times at lower temperatures and for dft's above 125 microns Do not apply or cure below 5°C Colour changes can occur in exposed conditions and will occur at elevated temperatures 														
<p>Health & Safety</p>	<p>Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.</p>														

The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.