technical data



Farmline Gloss Finish

Issue Date: Jan 2019 Reference: SP Page 1 of 2

Product Description	A high quality, single pack, modified-alkyd gloss finish for agricultural equipment and vehicle exteriors.									
Features & Use	 For interior and exterior use on previously painted metal and other substrates For application to agricultural plant and machinery Recommended for use with Farmline Primer For brush, roller or spray application 									
Approvals/ Certification	Please consult Axalta Coating Systems									
Finish	Gloss									
Volume Solids	45 ± 2% (varies with colour)									
VOC Content	435 ± 20 g/litre (varies with colour)									
Film Thickness Range And Coverage		Dry Film Thickness		Wet Film Thickness		Theoretical Coverag				
	Typical	30 µm		67 μm		15.0 m ² /litre				
	Practical coverage depends on the application method, painting conditions and the shape and roughness of the surface to be coated									
Drying Times	Applied to 30 microns DFT			+10°C		3°C +35°C				
	Dust Free		2½ hr		1½ hr		1 hr			
	Hard Dry		9 hr		6 hr		4 hr			
	Overcoating	Minimum		14 hr			8 hr			
	Drying and recoating times are related to the film thickness, temperature, the relative humidity of the air and ventilation									
Colours	BS, RAL and manufacturers shades to order									
Product Code	02FAR									
SG	0.98 kg/lt (varies with colour)									
Storage Conditions	Store in dry, cool conditions and protect from frost									
Shelf Life	Minimum 12 months if stored as above in unopened containers									
Flash Point	23-60°C									



Issue Date: Jan 2019 Page 2 of 2

Farmline Gloss Finish

Surface Preparation	 This product is a finish coat and should be applied over an appropriate primer and/or intermediate coat such as Farmline Primer or Farm Oxide Sheen All surfaces to be coated should be dry and cleaned as necessary to remove all oil, grease, salts, weld flux or other contamination 								
Mixing	Must be mixed thoroughly by using a mechanical agitator before use. Agitate periodically to ensure paint remains homogeneous.								
Thinner / Cleaner	Axalta Thinner TH400 (formerly called No.3 Thinner)								
Application Conditions	Only apply in conditions of good ventilation which must be maintained during drying and curing. Do not apply when rain, mist, sleet or snow are imminent. During application and drying time of the paint coating, the surface should be dry, the Relative Humidity should not exceed 85% and the steel temperature should remain at least 3°C above the dew point. Paint temperature should ideally be at a minimum of 15°C.								
Application Methods	Method	Airless Spray	Conventional Spray	Brush	Roller				
		Yes	Yes	Yes	Yes				
	 Brush/roller application is recommended – use as supplied For spray application, first consult the product Safety Data Sheet (SDS) and ensure compliance with all safety requirements Conventional spray: use up to 15% of TH400 Thinner, 50-60psi pressure and 1.4-1.8mm diameter nozzle Airless spray: use up to 10-15% of TH400 Thinner, with 1800-2200psi pressure and 11-15 thou tip (0.28-0.38mm) 								
Product Notes	 2 coats of Farmline Gloss are recommended for best results This product is white spirit based, only overcoat with other white spirit based products (with itself is recommended) Overcoating – maximum overcoating time is indefinite if clean and sound, but for best results overcoating within 48 hours (with itself) is recommended (at 20°C) Colours such as bright yellows, reds and oranges have lower opacity, especially when produced using lead-free pigments. Two or three coats of these shades may be required for solid coverage, relative to only one coat of, say, a grey or red oxide 								
Health & Safety	Containers are provided with safety labels which should be observed. Further information about hazardous influences and protection are detailed in individual Product Safety Data Sheets. A Safety Data Sheet for this product is available on request from Axalta Coating Systems.								

AN AXALTA COATING SYSTEMS BRAND



The information provided herein corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience becomes available. The data provided fall within the normal range of product properties and relate only to the specific material designated; these data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits or used alone as the basis of design; they are not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Axalta cannot anticipate all variations in actual end-use conditions Axalta makes no warranties and assumes no liability in connection with any of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights. This product is for professional use only.